

tripla coustics

YOUR SILENT PARTNER

TECHNICAL DATA SHEET

type Vo wall-ceiling



MATERIAL COMPOSITION



Top layer	Bico acou absorbing PET panel 7mm mottled grey color
Core	MDF black water repellent or fire retardant 9mm, 44.2% perforated and acoustic absorbing glass fibre tissue on the back
WEIGHT	7 kg/m ²

STANDARD DIMENSIONS FULL PANEL

	(square-sawn) 3030x640x±16 mm
Core	PET acou Panel ±12mm, 2400 gr/m ² [European fire class core B]

TEST SET-UP
IN LABORATORY:

**TOTAL THICKNESS
WALLS
86 mm**





f(Hz)	α_p
125	0,45
250	0,95
500	1,00
1000	0,95
2000	0,90
4000	0,90

Totale Thickness	% perfo	α_w	f(Hz)	Sound class	NRC	SAA
86 mm		0,95		A	0,95	0,93
Installation	Mounted on a wooden frame with a thickness of 70 mm, filled with 50 mm of mineral wool with a density of 40 kg/m ³ .					
Values according to reverberation room test EN ISO 354:2003 - EN ISO 11654:1997						

TEST SET-UP
IN LABORATORY:

**TOTAL THICKNESS
WALLS
36 mm**





f(Hz)	α_p
125	0,10
250	0,40
500	0,75
1000	0,90
2000	0,95
4000	0,90

Totale Thickness	% perfo	α_w	f(Hz)	Sound class	NRC	SAA
36 mm		0,70		B	0,75	0,74
Installation	Mounted on a wooden frame with a thickness of 20 mm, filled with 20 mm PRIMAWOOL of 22,5 kg/m ³ .					
Values according to reverberation room test EN ISO 354:2003 - EN ISO 11654:1997						

TEST SET-UP
IN LABORATORY:

**PRODUCT DIRECTLY
MOUNTED ON WALL/
CEILING**

f(Hz)	α_p
125	0,05
250	0,10
500	0,25
1000	0,50
2000	0,70
4000	0,85

Totale Thickness	% perfo	α_w	f(Hz)	Sound class	NRC	SAA
16 mm		0,30		D	0,40	0,40
Installation	Acoustic panels mounted directly onto wall/ceiling without plenum					
Values according to reverberation room test EN ISO 354:2003 - EN ISO 11654:1997						

installation full panels & planks

Fastening on single or double-spaced wooden battens (max 600 mm spacing) can be with underlying mounting laths (slant lath). These are screwed and/or glued to the back of the panels and the counter batten is fitted to the rear wall or on the framework.

Types Ms, Ns, Ls and Ls m can also be fixed by gluing at the back or by using a black screw at the front. Glueing can be done with an MS polymer adhesive sealant. First a primer is applied and then MS polymer.

The front side can also be mounted with black screws in case e.g. ceiling fixing /assured fixing is required. In the openings of the framework, a sound-absorbing sound-absorbing material (e.g. rock wool or Primawool) should be placed .



The 4 sides of the board must always be supported by the battens.

For impact-sensitive areas, we recommend longitudinal connections of 2 panels to an underlying common batten with 2 to 3 mm spacing.

End connections of 2 panels are mounted on a common underlying common battens with an intermediate joint of 2 to 3 mm. A space should be provided at the top between the panel and the ceiling to allow you to hook the panel into the slant lath.


We recommend working with a clearance of at least 1 mm per running metre to allow for possible expansion; and this over the total height and/or width of the wall.

On request, you can receive specific installation instructions and certificates for: walls where increased impact is likely (sports halls venues, ...) in accordance with standard ETAG 003 & EN 13964 and for ceiling mounting.




TEST SET-UP
IN LABORATORY:
**TOTAL THICKNESS
WALLS**
88/90 mm

**TOTAL THICKNESS
WALLS**
38/40 mm




inspiration corner + plinths


Corner solutions



Wall connections




Floor connections



*

Ceiling LED line




- Primawool or rockwool
- Triplacoustics panel
- wooden structure
- wall
- profile available at specialist shop
- decorative full panel material or massive wood
- LED line

* Required plinth position in case of type F or Ds

installation patterns

There are different possible installation patterns for panels and planks.
A couple of examples of patterns with planks are given in the drawings below.



Primawool®

Description

- > Low density absorber
- > 100% polyester fibre
- > 1-sided drum membrane: white
- > Colour of polyester fibre: white
- > Applications: walls, ceilings and baffle filling

Features

- > 100 % recyclable PET
- > Inodorous
- > No emission of volatile organic compounds (VOCs) (A+ level)
- > Moisture and rot resistant
- > Non irritating for skin and eyes
- > European fire class B-s2-d0


Figures

Density ISO 9073-1
 Thickness E0 (without load) ISO 9073-2
 Thickness E1 (load of 50g/50cm²)
 Thickness E10 (load of 500g/500cm²)
 Inflammability FMVSS 302
 Dimensions of roll (length / width / width tolerances)
 Package

450 gr/m²
 22 mm (measured without package)
 21 mm (measured without package)
 13 mm (measured without package)
 <100 mm/min (self-extinguishing)
 30 m / 600 mm / -0 +2 cm
 36 m² (2 separate rolls of 30 m)


Acoustic features

Absorption coefficient is determined by measuring a sample of PRIMAWOOL® in the reverberation room.



Installation PRIMAWOOL®

Installation in a framework with vertical or horizontal slats.




made-to-measure solutions



Akoest-object

You can also opt for acoustic baffles to absorb the sound in a room. These baffles are available as individual wall or ceiling elements. They can be made to measure on the basis of all our types.



Akoest-lambris

All walls/ceilings are available in woodpanelling non acou on request
 > 0% Perforation (no absorption)
 > On full black core board
 Can be used as outer corner panel



Akoest-box-type

On request, we can deliver frames (colour-coordinated or otherwise) in veneer, HPL or solid timber on various depths and widths. Assembled or loose.



storage and handling of finished panels

The acoustic panels/planks can be mounted horizontally and vertically. For conditioning, we recommend to store the panels in the room at least 48 hours before mounting them. These panels are by nature and composition only to be mounted in a well-conditioned room with a relative humidity between 35 and 55 % and a temperature between 14 and 30 °C. Large temperature and humidity differences between front and plenum are not allowed.

Flat storage with larger cover plate

Handle with care (delicate panels)

Larger cover plate than the Triplacoustics® panels.






felt panels

Specific to Bicooustics range is that the Core consists of a black rigid acoustic PET sheet made of more than 50% Postconsumer recycled PET fibres.



These bicomponent fibres (soft melt jacket with hard long fibre Core), are hot-pressed into rigid acoustic boards measuring 3050 x 1300mm x ± 12mm.

These boards are light, stiff and absorb incident sound molecules very well and are therefore very suitable as core material for our acoustic panels. These boards have a fire reaction class B-s1-d0.




TYPE	NAME	TOP LAYER	DIMENSIONS	ALPHA W	ALPHA W	ALPHA W	
			(± mm)	70 mm frame	20 mm frame		PAGINA IN CATALOGUS
				50 mm Rockwool	20 mm Primawool	Directly installed on the wall- ceiling	
				wall- ceiling	wall- ceiling		



GROOVED

	Transversal core wide blade	HPL veneer	3030 x 640 x ±14 3030 x 592 x ±14	0,95	0,70	0,25	see page 86
				0,95* 0,95**	0,80* 0,78**	0,40* 0,43**	
	Transversal core Broad blade	HPL veneer	3030 x 640 x ±14 3030 x 576 x ±14	0,85	0,80	0,35	see page 88
				0,90* 0,95**	0,80* 0,78**	0,55* 0,53**	



MICRO/NANO

	Micro	HPL veneer	3030 x 630 x ±14 3030 x 600 x ±14	1,00	0,70	0,25	see page 92
				0,95* 0,95**	0,80* 0,79**	0,40* 0,43**	
	Nano	HPL veneer	3030 x 630 x ±14 3030 x 600 x ±14	0,95	0,70	0,30	see page 94
				0,95* 0,94**	0,80* 0,79**	0,40* 0,44**	

SLATS

		HPL veneer	3030 x 624 x ±22	0,95	0,80	0,35	see page 98
				0,95* 0,93**	0,80* 0,80**	0,55* 0,56**	
		Oak-Rubberwood solid FJ	3030 x 637 x ±30	0,95	0,80	0,40	see page 100
				0,90* 0,92**	0,80* 0,81**	0,60* 0,59**	

V MONO

			3030 x 640 x ±16	0,95	0,70	0,30	see page 104
				0,95* 0,93**	0,75* 0,74**	0,40* 0,40**	
		RAL / NCS	3030 x 640 x ±16	0,95	0,70	0,30	see page 106
				0,95* 0,93**	0,75* 0,75**	0,40* 0,40**	

* NRC (Noise Reduction Coefficient): arithmetic average of measured sound absorption coefficient alphas at frequency levels of 250, 500, 1000 and 2000 Hz.

** SAA (Sound Absorption Average): arithmetic average of measured sound absorption coefficient alphas at frequency levels of 200 up to 2500 Hz.

tripla coustics

YOUR SILENT PARTNER

PRINT
ACOUSTICS

WOOD
COUSTICS

BI
COUSTICS

Triplacoustics is a TRIPLACO brand

Generaal Deprezstraat 2, 8530 Harelbeke - Belgium

T +32 56 22 62 17 | F +32 56 22 98 15 | info@triplacoustics.be | www.triplacoustics.be